

Research Article

Journal of Biopolymers and Theoretical Studies

Hydrophilic-Hydrophobic Copolymers of Functional-Ph-Responsive, and Post Polymerization

Momen SA Abdelaty

Polymer Lap, Chemistry Department, Faculty of Science (Assiut), Al-Azhar University, Assiut, 71524, Egypt

*Corresponding author:

Momen SA Abdelaty, Polymer Lap, Chemistry Department, Faculty of Science (Assiut), Al-Azhar University, Assiut, 71524, Egypt

Submitted:18 Oct 2021; Accepted:28 Oct 2021; Published:05 Nov 2021

Citation: Momen SA Abdelaty (2021) Hydrophilic-Hydrophobic Copolymers of Functional-Ph-Responsive, and Post Polymerization. J Biop Theo Stud 1(1): 07-13.

Abstract

4-hydroxy-3-methoxy benzaldehyde or Vanillin was used for preparing tertiary amine cationic monomer. The monomer has been used as pH-responsive and the functional aldehyde group was used for the formation of Schiff base. The new monomer was abbreviated by DEAMVA and investigated using chemical analysis e.g. 1H NMR, 13C NMR and FT IR all data were in logic case. The copolymerization of Styrene with 10 and 25 mol% of DEAMVA has been implemented by free radical polymerization. The copolymers have been chemically and physically evaluated e.g. 1H NMR, FT IR, GPC, and DSC. Post polymerization modification of copolymer with 25 mol% (III b) was fabricated via the immobilization with Tryptophan, and has also been investigated by the same instrument used lately. Moreover, the responsive property of the posted polymer to pH has also been tested by UV-vis. Spectroscopy.

Keywords: PH-Responsive, Functional Polymer, Hydrophilic-Hydrophobic, Vanillin, Amino Acid, Post-Polymerization

Introduction

Environmentally pH-responsive polymers are kind of polyelectrolytes that have acidic or basic groups in their main chain and either can donate or withdraw protons in response to changes in pH of media [1,2]. The charge along the polymer chain is responsible for the electrostatic repulsion that increases in the hydrodynamic volume of the polymer molecules [3,4]. Such kind of transition between tightly coiled and swollen state is affected by any condition that modify the electrostatic repulsion, e.g. pH, ionic strength, and type of counter ions. The transition state from collapsed into expanded was explained by changes in the osmotic pressure exerted by mobile counter ions and has been neutralized the network charges [2]. Many applications for pH-responsive polymers with the greatest interest in biomedicine e.g. Drug delivery systems and Gene carriers [5-11].

In the last few decades many scientists were looking for green alternatives of styrene monomer due to its disadvantages like, hazardous air pollutants and emitting during metering mixing process and curing; moreover, the unreacted styrene continues to be released from composites during life cycle [12]. They focused their research in the renewable resources e.g. cellulose, starch, natural oil...etc. they have been performed as alternative to produce biobased monomers [13]. The lignin produced from Vanillin becoming relatively easily accessible; still there are only a handful of reports on attempts to utilize vanillin as monomers for bio-based polymer synthesis [14,15]. The chemical modifications on vanillin have implemented attributed to the presence of both aldehyde and hydroxyl active groups [2,16]. It exposed to dimerization and polymerization process via electrochemical reductive with horseradish peroxidase [17].

Schiff's base was used in the coordination chemistry and was found to be stable under redox conditions [18]. Recently, vanillin was used to form Schiff bases [19]. Their biological activities have been widely reported in many publications [20-24]; the most useful articles by Yuan et al., they used Schiff base as a stimuli-responsive linker in the polymer chain [25]. The imine linkage is pH-responsive [26,27]. Moreover; the complexes formation of the imine has also been used to achieve the pH-responsiveness of the linker [28-33]. Several articles have reported "click reaction" as linkers for many bio-based molecules [34-36]. In this work, we fabricated new pH-responsive polystyrene copolymers from vanillin as renewable resource. The aldehyde group was used for post-ing biomolecule by Schiff base.

Experimental Material

(AIBN Acrōs) 2,2'azobis(isobutyronitrile) was recrystallized from methanol, acryloyl chloride (98% Merck), vanillin (99% Acrōs), styrene (99% Acrōs), triethylamine (Merck), tryptophan (97 % Acrōs). Toluene, dichloromethane, tetrahydrofuran, and diethyl ether were distilled. Other chemicals were used as purchased.

Instruments

Bruker AV 500 spectrometer was used to record 1H and 13C NMR spectra in CDCl3 or DMSO-d6 at 500 MHz and 125 MHz FT IR Vertex 70 Fourier transform infrared instrument for recording IR spectra. The Molecular weights (M) and dispersity (Đ) were analysed by size exclusion chromatography (SEC). Chloroform was used as eluent (containing of 0.1 vol% triethylamine). UV/ vis spectroscopy (Perkin Elmer Lambda 45) was used to estimate the concentration of amino acid in post-polymer. The pH of polymer solution was in THF and measured by pH-meter model VWR pH100. Perkin Elmer Differential Scanning Calorimeter (DSC) Pyris 1 was used for the glass temperature Tg of solid polymers at heating and cooling rate of 5 °C/min.

Synthesis of Monomer: Synthesis of 2-[(diethylamino)methyl]-4-formyl-6-methoxy-phenyl acrylate (DEMAVA) [20].

Step-1: Synthesis of 3-[(diethylamino) methyl)-4-hydroxy-5-me-thoxybenzaldhyde [20]

10g (0.065 mol) of vanillin, (4-hydroxy-3-methoxy benzaldehyde), 10g (0.33 mol) of formaldehyde and 10g of diethylamino (0.136 mol) were dissolved in 150 mL ethanol in 250 mL round bottomed flask fitted with reflux condenser. They were refluxed in oil bath at 90-100 °C for 3 h. The mixture allowed cooling to room temperature. The solvent was removed under reduced pressure to collect the product. Yield %: 97%, Physical state: Yellowish white solid.

¹H NMR (500 MHz, CDCl₃): δ (ppm) = 1.18(t, 6H.12-CH₃), 1.26 (br., s, 1H, 8-OH), 2.73 (q, 4H, 11-CH₂), 3.92 (s, 2H, 9-CH₂), 3.94 (s, 3H, 7-CH₃), 7.25, 7,34 (dd, 2H, ⁴J = 1.6, 3,3-- Ar-CH, 10-NH⁺), 9.77 (s,1H, 1-CHO).

13C-NMR (125 MHz, CDCl3): δ (ppm) =10.82 (2C, 12-CH3), 46.35 (2C, 11-CH2), 55.85 (1C, 10-CH2), 56.01 (1C, 8-CH3),109.68 (1C, 4--Ar-CH), 120.84 (1C, 4-Ar-CH), 125.75 (1C, 5-Ar-C), 127.99 (1C, 3-Ar-CH), 148.65 (1C, 6-Ar-CH), 154.87 (1C,7-Ar-C), 191.65 (1C, 2-C=O).

IR (KBr): v (cm⁻¹): 2987 (s) (CH₂, CH₃), 1650 (s) (2-C=O₃), 1706 (s) (7-C=O), 820- 868 (m) (Ar-CH).

Step-2: Synthesis of 2-[(diethylamino) methyl]-4-formyl-6-me-thoxyphenyl acrylate [20]

13.9g (0.058 mol) of 3-[(diethylamino) methyl)-4-hydroxy-5-methoxybenzaldhyde (I) was dissolved in 200 mL dry CH₂Cl₂ in two neck flasks fitted with argon balloon. During stirring 12.3g (0.12 mol) of TEA was added. The reaction mixture allowed cooling in ice bath to 0-5oC. After cooling, 5.4g (0.059 mol) acryloyl chloride was added drop wise. The yellowish suspension was stirred at 5oC for 1h, and then allowed to stir at RT for 6 h. The precipitate

was filtered and solvent was evaporated under reduced pressure. The product was extracted by CH2Cl2 and wash three times with 100 ml distilled water then one time with 0.1M Na2CO3, and again with 100 ml distilled water, then product dried with MgSO4 overnight. Yield %: 80%, Physical state: Orange solid.

¹H NMR (500 MHz, CDCl₃): δ (ppm) = 1.10(t, 6H.14-CH₃), 2.48 (q, 4H, 13-CH₂), 3,51 (s, 2H, 11-CH₂), 3.88 (s, 3H, 7-CH₃), 6.06 (dd, ²J = 1.3 Hz, ³J = 10.40 Hz,1H, 10a-CH), 6.37(dd, ³J = 10.40 Hz, ³J = 17.30 Hz, 1 H, 9-CH), 6.63 (dd, ²J = 1.3 Hz, ³J = 17.30 Hz, 10b-CH), 7.25, 7.34 (dd, 3H, ⁴J = 1.6, 4J = 1.9, 3,3-- Ar-CH), 9.77 (s,1H, 1-CHO).

¹³C-NMR (125 MHz, CDCl₃): δ(ppm) =10.82 (2C, 12-CH₃), 46.35 (2C, 11-CH₂), 55.85 (1C, 10-CH₂), 56.01 (1C, 8-CH3),109.68 (1C, 4--Ar-CH), 120.84 (1C, 4-Ar-CH), 125.75 (1C, 5-Ar-C), 127.99 (1C, 3-Ar-CH), 148.65 (1C, 6-Ar-CH), 154.87 (1C,7-Ar-C), 191.65 (1C, 2-C=O).

IR (KBr): v (cm⁻¹): 2987 (s) (CH₂, CH₃), 1650 (s) (2-C=O,), 1706 (s) (8-C=O,), 820- 868. (m) (Ar-ČH).

Synthesis of Polymer

Synthesis of poly (Styrene-co-DEAMVA) with 10 and 25 mol% of DEAMVA (2a)

A mixture of 10 and 25 mol%, 1.088 g, and 2.176 g respectively of 2-[(diethylamino) methyl]-4-formyl-6-methoxyphenyl acrylate, 4 g (0.038 mol) styrene and 10-3 mol% AIBN of the total mole% of monomers was dissolved in 70 ml toluene and then added to 100 ml round bottom flask. They were purged with argon for 15 min., and then heated in an oil bath at 70-80°C with continuous stirring for 6 h. After cooling at room temperature followed in refrigerator, and was precipitated by solvent evaporation using rotatory evaporator. Polymer was purified by dissolved in THF, and re-precipitated in diethyl ether to remove the unreacted monomers and impurities. Yield %: 91%, and 82 for 10, and 25 mol% respectively, Physical state: Yellowish white solid.

¹H NMR (500 MHz, CDCl₃): δ (ppm) = 0.50-2.71 (m, 9H, CH, CH₂-styrene repeating unit, 2CH3 DEAMVA), 3.25-3.93 (m, 9H, 2CH2, NCH2, OCH3 DEAMVA), 4.60-5.13 (m, 3H, CH, CH₂-DEAMVA repeating unit), 6.30-7.52(m, 6H, H-Ar), 9.75-9.97 (br., 1H, -CHO).

IR (KBr): v (cm⁻¹): 2990(s) (CH-Aliphatic), 1720-1743 (s) (-C=O), 1134 (s) (-OCH₂).

Synthesis of 25 mol% (2a-25) Poly (Styrene-co-DEAM-VA)-post-tryptophan (2b) as a function of pH-responsive

In 50 ml round bottom flasks 1.0 g of 25 mol% poly (Styrene-Co-DEAMVA) and 1.0 g of tryptophan has been dissolved in 30 ml THF. The reaction was implemented in different pH solutions pH4, pH7, pH9, pH10, pH12 by addition of NaOH and HCl. The mixtures were stirred gently for 2 h at room temperature. Solvent was removed under reduced pressure. After that the precipitate was dissolved in THF and re-precipitate in diethyl ether at -400 C to remove impurities and unreacted molecules. Physical state: Brownish solid. ¹H NMR and IR of poly (Styrene-co-DEAMVA)-post-Tryptophan at pH12 (IV)

¹H NMR (500 MHz, DMSO): δ (ppm) = 0.70-1.22 (m, 6H, 2CH₃, DEAMVA), 1.30-1.65 (m, 1H, CH repeating Styrene), 1.82-2.35 (m,2H, CH2 repeating styrene), 2.80-2.90(m, 2H, 2NCH2, DE-AMVA), 3.30-3.40 (m, 2H, CH2, DEAMVA), 6.10-6.34(m, 1H, C=CH, Tryptophan), 6.80-7.85(m, 9H, H-Ar), 8.5-8.6 (br. (s),1H, CH=N), 9.30-9.942 (s) 1H, NH, Tryptophan).

IR (KBr): v (cm⁻¹): 2995(m) (CH-Aliphatic), 1663-1650 (s) (7-C=O), 1570-1560 (s) (4-CH=N), 1026-1107 (s) (8-OCH₂).

Results and Discussion

Synthesis of Monomer, copolymers and grafted copolymers

The chemical procedure has been described in Scheme 1. Monomer (1b) or 2-[(diethylamino) methyl]-4-formyl-6-methoxyphenyl acrylate (DEAMVA); it was prepared in two steps. The first is the preparation of (3-[(diethylamino)methyl)-4-hydroxy-5-methoxybenzaldehyde) and has been occurred by the reaction of vanillin with diethylamine and formaldehyde according to Mannich reaction mechanism [1,20]. The second is the preparation of 2-[(diethylamino)methyl]-4-formyl-6-methoxyphenyl acrylate (DEMA-VA). It has been performed by the reaction of compound (1a) with acryloyl chloride and TEA to form (1b). They have been chemically investigated by 1H NMR and 13C and FT IR. Figure 1-3 proved all data and in logic state and has also been proved the presence of aldehyde group at 9.97 ppm and 196 ppm.

To optimize the general properties of styrene by free radical copolymerization with 10 and 25 mol% of DEAMVA were used in AIBA as initiator as Scheme 1. The chemical structure was estimated by 1H NMR and FT IR as shown in Figure 4. The 1HNMR of copolymers 1a, 2a demonstrated specific broad multiples peaks at $\delta = 0.73$ -1.35 ppm of 2CH3 DEAMVA, at $\delta = 7.08$ -7.62 ppm of Ar-H of each styrene and DEAMVA, and at $\delta = 9.94$ of H-CHO of DEAMVA monomer. FT IR illustrated the presence of (C=O stretch) ester at 1745 cm-1. The actually content of each monomer in the polymer main chain was detected from 1H NMR spectra via the determination of the ratio of the intensity of the signals at 6.66 ppm (for H, Ar-H styrene) with signal at 9.94 ppm (for CHO of DEAMVA) as written in Table 1.

The aldehyde functional group in the polymer main chain was used for posting with any primary amino compound producing Schiff's base as in Scheme 1. The post-polymerization process was fabricated at room temperature in THF at different pH (pH4, pH7, pH9, pH10, pH12). Post-copolymer was investigated by 1H NMR and FT IR. The 1H NMR demonstrated the disappearance of aldehyde signal at 9.74 ppm and formation of new amino (HC=N) signal at about 8.5 ppm as in Figure 3. Figure 4 showed FT IR spectra that proved the presence of imine (C=N stretch) at about 1563 cm⁻¹.



Scheme 1: Synthesis of new monomer, copolymers and post-polymer with Tryptophan.

Table: Yield, composition, conversation, number average molecular weight, polydispersity, and glass temperature of, Poly (S-co-DEAMVA) 10, 25 mole ratios of DEAMVA and Poly (S-co-DEAMVA)-post-try.

Polymer	Yield (%)	¹ HNMR DEAMVA (mol %)	Conversion (%)	Mn a (g/mol)104	Đ Þ	Tg c (°C)
2a-10	91	6.35	-	44600	1.88	114
2a-25	82	17.67	-	17760	2.04	134
2b	76	-	84	15458	2.38	139

a Number average molecular weight,

b Polydispersity,

c Glass transition temperature,

d Lower critical solution temperature.





Figure 3: ¹H NMR spectra (CDCl3) of P(S-co-DEAMVA) 10, 25 mole ratio of DEAMVA



Figure 4: 1H NMR spectra (DMSO) of P(styrene-co-DEAM-VA)-g-Tryptophan



Figure 5: IR spectra KBr for DEAMV (I), DEAMVA (II), Poly (Styrene-co-DEAMVA) (III b) and grafted copolymers IV.

Polymer characterization Molecular Weight

Size exclusion chromatography was used for determination of number average molecular weight (Mn) and dispersity (Đ) of polymers using Polystyrene (PS) as standard in CHCl3. Table 1 summarized all recorded data for all copolymers. Figure 6 shows the relation between molecular weight and log M as recoded by GPC and demonstrated one peak, that demonstrated the disappearance of low molecular weight like monomers or impurities.



Figure 6: GPC molecular weight of copolymers

Conversion of poly (Styrene-Co-DEAMVA) to poly (Styrene-Co-DEAMVA)-g-tryptophan

The conversion of poly (Styrene-Co-DEAMVA) to poly (Styrene-Co-DEAMVA)-post-tryptophan by the chemical reaction, absorption was measured as function with pH at constant time (2h) for each test. The polymer solution was diluted to 10-3 W/V for each run. Figure 7 illustrates the UV.vis. Spectroscopy of post reaction between poly (Styrene-Co-DEAMVA) with tryptophan. We noticed the disappearance of C=O aldehyde group at 250-270 nm and formation of new bond at 340-380 nm of C=N imine linkage. The formation of amino linkage has increased with increasing the pH value starting with pH5 which showed about zero absorbance and has been increased gradually till the highest value of absorbance pH12. Figure 8 shows the relation between pH and absorbance intensity at constant time.



Figure 7: UV-vis. Spectroscopy for the formation of grafted poly (Styrene-Co-DEAMVA)-post-tryptophan as increasing in absorbance from pH5-pH12.



Figure 8: Relation between pH values and absorbance

Glass Transition Temperature

The glass transition temperature (T_g) was measured for all polymers. It was detected by Differential Scanning Calorimeter at heating rate 50 C/min. It was recoded as the mid-point inflection in the thermogram. They have been tabulated in Table 1 for copolymers

and post-copolymer. a single T_g for each sample, which indicating the formation of random copolymers as shown in Figure 9 [36]. The T_g of the homo-polystyrene (PS) showed at 100oC [37]. Copolymerization with DEAMVA change the hydrophobic and hydrophilic groups demonstrated in aromatic and tertiary amine respectively that increased T_g , which attributed to decrease in the spacing and therefore increasing in the interaction between polymer chains producing lesser flexibility and T_g of the polymer increased [36]. By introducing post molecule in copolymer (2b) main chain has directly influenced on raising the T_g due to the steric hindrance of aromatic molecule.



Figure 9: DSC shows the Tg of copolymers and grafted copolymer

Conclusion

We prepared functional polystyrene copolymers. The pH-responsive monomers have tertiary amine and aldehyde groups, and were prepared in two steps. We used free radical polymerization of styrene with two mole ratios of new monomer was for fabricating copolymers. The post-polymerization was created by the reaction of aldehyde group with primary amine. Tryptophan was used post-polymerization. The uv.vis. Spectroscopy was used for detecting the post-polymer formation through the Schiff base absorption at different pH values. The highest absorption at pH12 and lowest at pH4 have been observed.

Acknowledgment

The authors are grateful acknowledge to Egyptian culture and missions, and The Deutscher Akademischer Austauch (DAAD) for financial assistance during the post doctor work in Germany of Momen SA Abdelaty.

References

- 1. Momen SA Abdelaty (2018) Poly (N-isopropylacrylamide-co-2-((diethylamino)methyl)-4 formyl-6-methoxyphenylacrylate) Environmental Functional Copolymers: Synthesis, Characterizations, and Grafting with Amino Acids. Biomolecules 8: 1-17.
- Abdelaty MSA, Kuckling D (2016) Synthesis and Characterization of New Functional Photo Cross-Linkable Smart Polymers Containing Vanillin Derivatives. Gels 2: 1-13.
- 3. Sato E, Masuda Y, Kadota J, Nishiyama T, Horibe H (2015) Dual stimuli-responsive homopolymers: Thermo and photo-responsive properties of coumarin-containing polymers in organic solvents. Eur Polym J 69: 605-615.

- Abdelaty MSA (2018) Environmental Functional Photo-Cross-Linked Hydrogel Bilayer Thin Films from Vanillin. J Polym Environ 26: 2243-2256.
- 5. Abdelaty MSA(2021) Trends in the Phase Separation Temperature Optimization of a Functional and Thermo-pH Responsive Terpolymer of Poly (N-isopropylacrylamide-co-N-(2-(dimethylamino)ethyl) Acrylamide-co-vanillin Acrylate). J Polym Environ 29: 3116-3129.
- Abdelaty MSA (2018) Preparation and Characterization of New Environmental Functional Polymers Based on Vanillin and N-isopropylacrylamide for Post Polymerization. J Polym Environ 26: 636-646.
- 7. Kocak G, Tuncer C, Bütün V (2017) PH-Responsive polymers. Polym Chem 8: 144-176.
- Abdelaty MSA, Kuckling D (2021) Altering of lower critical solution temperature of environmentally responsive poly (N-isopropylacrylamide-co-acrylic acid-co-vanillin acrylate) affected by acrylic acid, vanillin acrylate, and post-polymerization modification. Colloid Polym Sci 299: 1617-1629.
- 9. Ankit K, Carlo M, Hyo-Jick C (2017) Smart Microparticles with a PH-responsive Macropore for Targeted Oral Drug Delivery. Scientific Reports 7: 3059-3067.
- Lin L, Wen Dong Y, Yue Feng R, Xiao Yang L, Jian Qing G (2017) PH-Responsive carriers for oral drug delivery: challenges and opportunities of current platforms. Drug Delivery 24: 569-581.
- 11. Jing X, Anqi L, Jianshu L (2017) Advances in pH-Sensitive Polymers for Smart Insulin Delivery. Macromol Rapid Commun 38: 1-14.
- 12. Chen G, Hoffman AS (1995) Graft copolymers that exhibit temperature-induced phase transition over a wide range of pH. Nature 373: 49-52.
- Hoffman AS, Stayton PS, Bulmus V (2000) Really smart bioconjugates of smart polymers and receptor proteins. J Biomed Mater Res 52: 577-586.
- Abdelaty MSA (2021) Poly(N-isopropylacrylamide-co-2-((diethylamino)methyl)-4-methylphenyl acrylate) thermo-ph responsive copolymer: trend in the lower critical solution temperature optimization of Poly (N-isopropyylacrylamide). J Polym Res 28: 213.
- 15. Abdelaty MSA (2019) Influence of vanillin acrylate and 4 acetylphenyl acrylate hydrophobic functional monomers on phase separation of N isopropylacrylamide environmental terpolymer: fabrication and characterization. Polym Bull 77: 2905-2922.
- 16. Fache M, Darroman E, Besse V, Auvergne R, Sylvain Caillol, et al. (2014) Vanillin, a promising bio-based building-block for monomer synthesis. Green Chem 16: 1987-1998.
- 17. Ananda SA, Bernard W, Ashfaqur R (2012) Vanillin based polymers: I. An electrochemical route to poly vanillin. Green Chem 14: 2395-2397.
- Ananda S A, Ashfaqur R (2012) Vanillin-Based Polymers-part II: Synthesis of Schiff Base Polymers of Divanillin and Their Chelation with Metal Ions. ISRN Polymer Science 1: 1-5.
- Abdelaty MSA (2018) Environmental Functional Photocross-linked Hydrogel Bilayer Thin Films from Vanillin (Part 2): Temperature responsive layer A, Functional, Temperature and pH layer B. Polym Bull 11: 4837-4858.
- 20. Abdelaty MSA (2018) Preparation and Characterization of

Environmental Functional Poly (Styrene-Co-2-[(Diethylamino)Methyl]-4-Formyl-6-Methoxy-PhenylAcrylate) Copolymers for Amino Acid Post Polymerization. Open Journal of Polymer Chemistry 8: 41-55.

- 21. Firdaus M, Meier MAR (2013) Renewable copolymers derived from vanillin and fatty acid derivatives. Eur Polym J 49: 156-166.
- 22. Mialon L, Vanderhenst R, Pemba AG, Miller SA (2011) Polyalkylenehydroxybenzoates (PAHBs): Bio renewable Aromatic/Aliphatic Polyesters from Lignin. Macromol Rapid Commun 32: 1386-1392.
- Abdelaty MSA, Kuckling D. (2018) Poly (N-Isopropyl Acrylamide-Co-Vanillin Acrylate) Dual Responsive Functional Copolymers for Grafting Biomolecules by Schiff's Base Click Reaction. Open Journal of Organic Polymer Materials 8: 15-32.
- 24. Abdelaty MSA (2019) Layer by Layer Photo-Cross-Linked Environmental Functional Hydrogel Thin Films Based on Vanillin: Part 3. J Polym Environ 27: 1212-1225.
- 25. Abdelaty MSA, Kuckling D (2016) Synthesis and Characterization of New Functional Photo Cross-Linkable Smart Polymers Containing Vanillin Derivatives. Gels, 2: 1-13.
- Abdelaty MSA (2021) A facile Method for the Preparation of Hydrophilic-Hydrophobic Functional Thermo-pH Responsive Terpolymers Based on Poly (NIPAAm-co-DMAA-co-DMAMVA) and Post-Polymerization. J Polym Environ 28: 213.
- 27. Zhou L, Cai Z, Yuan J, Kang Y, Yuan W, et al (2011) Multifunctional hybrid magnetite nanoparticles with pH-responsivity, superparamagnetism and fluorescence. Polym Int 60: 1303-1308.
- 28. Lyas G, Burak A, Serkan K, Oguz Y S, Emel Y, et al. (2017) Synthesis of imine bond containing insoluble polymeric ligand and its transition metal complexes, structural characterization and catalytic activity on esterification reaction. Designed Monomers and Polymers 1: 441-448.
- 29. Etika KC, Cox MA, Grunlan JC (2010) Tailored dispersion of carbon nanotubes in water with ph-responsive polymers. Polymer 51: 1761-1770.
- Oda Y, Kanaoka S, Aoshima S (2010) Synthesis of dual pH/ temperature-responsive polymers with amino groups by living cationic polymerization. J Polym Sci Part A Polym Chem 48: 1207-1213.
- Yan Q, Zhou R, Fu C, Zhang H, Yin Y, et al. (2011) CO2-Responsive Polymeric Vesicles that Breathe. Angew Chem Int 50: 4923.
- Dondoni A, Marra A (2012) Recent applications of thiol–ene coupling as a click process for glycoconjugation. Chem Soc Rev 41: 573-586.
- Fu R, Fu G (2011) Polymeric nanomaterials from combined click chemistry and controlled radical polymerization. Polym Chem 2: 465-475.
- Franc G, Kakkar AK (2010) Click" methodologies: efficient, simple and greener routes to design dendrimers. Chem Soc Rev 39: 1536-1544.
- Iha RK, Wooley KL, Nyström AM, Burke DJ, Kade MJ, et al. (2009) Applications of orthogonal "click" chemistries in the synthesis of functional soft materials. Chem Rev 109: 5620-5686.

- 36. Gupta S, Kuckling D, kretschmer K, Choudhary V, Adler HJ (2007) Synthesis and characterization of stimuli-sensitive micro- and nanohydrogel based on photocrosslinkable poly (dimethylaminoethyl methscrylate). Journal of polymer science Part A Polymer Chemistry 45: 669-679.
- Part A Polymer Chemistry 45: 669-679.
 37. Mark James E (2009) Polymer data handbook (2nd Edition). Oxford University Press.

Copyright: ©2021 Momen SA Abdelaty. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.